



TAIRILAC[®] ABS RESIN

Property	Unit	Test Method	Test Condition	General Purpose Grade
				AG15A1
Tensile Strength	kg/cm ² (Mpa)	ASTM D-638 (ISO 527)	23 °C	460 (45)
Flexural Strength	kg/cm ² (Mpa)	ASTM D-790 (ISO 178)	23 °C	740 (73)
Flexural Modulus	kg/cm ² (Mpa)	ASTM D-790 (ISO 178)	23 °C	25000 (2450)
Rockwell Hardness	R-scale	ASTM D-785 (ISO 2039/2)	23 °C	R-110
Izod Impact Strength	kg-cm/cm (J/m)	ASTM D-256 (ISO R180)	23 °C 1/4"	22 (216)
Vicat Softening Point	°C	ASTM D-1525 (ISO 306)	1Kg load	100
Heat Deflection Temperature	°C	ASTM D-648 (ISO 75/A)	Unannealed 18.6 kg/cm ² (1/2"bar)	83
			Annealed (80°C×8hr)	93
Melt Flow Index	g/10 min	ASTM D-1238 (ISO 1133)	200°C×5kg(49N)	2.0
			220°C×10kg(98N)	20
Specific Gravity		ASTM D-792 (ISO 1183)	23°C/23°C	1.05
Flammability		UL-94	File No. E162823	1.5mm HB All Color
CHARACTERISTICS	Medium impact, High gloss			

All tests were run under laboratory conditions, ASTM, ISO testing procedures. The data are intended as a general guide only.

Formosa ABS Plastics (Ningbo) Co., Ltd.

TEL: (0574) 86028116/86028186 / FAX: (0574) 86029999-2116/2186

Address: FPG Ningbo Industrial Park Beliun Ningbo, China

Website: <https://en.fcfc-plastics.com/>

