

# SABIC® LDPE HP2023JN

## LOW DENSITY POLYETHYLENE

### DESCRIPTION

HP2023JN is a Low Density Polyethylene grade suitable for general-purpose packaging. It exhibits better draw down, good optical and mechanical properties. HP2023JN contains slip and antiblock additives.

### TYPICAL APPLICATIONS

Thin shrink film, lamination film, produce bags, textile packaging, soft goods packaging, general-purpose bags with good optics and t-shirts carrier bags.

### TYPICAL PROPERTY VALUES

Revision 20220720

| PROPERTIES                               | TYPICAL VALUES | UNITS    | TEST METHODS |
|--|----------------|----------|--------------|
| <b>POLYMER PROPERTIES</b>                |                |          |              |
| <b>Melt Flow Rate (MFR)</b>              |                |          |              |
| at 190°C and 2.16 kg                     | 2.0            | g/10 min | ASTM D1238   |
| <b>Density</b>                           |                |          |              |
| at 23°C                                  | 923            | kg/m³    | ASTM D1505   |
| <b>FORMULATION</b>                       |                |          |              |
| Slip agent                               | ☑              | -        | -            |
| Anti block agent                         | ☑              | -        | -            |
| <b>OPTICAL PROPERTIES <sup>(1)</sup></b> |                |          |              |
| Haze                                     | 8              | %        | ASTM D1003   |
| <b>Gloss</b>                             |                |          |              |
| at 45°                                   | 61             | %        | ASTM D2457   |
| <b>FILM PROPERTIES <sup>(1)</sup></b>    |                |          |              |
| <b>Tensile Properties</b>                |                |          |              |
| stress at break, MD                      | 20             | MPa      | ASTM D882    |
| stress at break, TD                      | 15             | MPa      | ASTM D882    |
| strain at break, MD                      | 300            | %        | ASTM D882    |
| strain at break, TD                      | 588            | %        | ASTM D882    |
| stress at yield, MD                      | 12             | MPa      | ASTM D882    |
| stress at yield, TD                      | 12             | MPa      | ASTM D882    |
| 1% secant modulus, MD                    | 235            | MPa      | ASTM D882    |
| 1% secant modulus, TD                    | 271            | MPa      | ASTM D882    |
| <b>Tear Resistance</b>                   |                |          |              |
| MD                                       | 15             | g/μm     | ASTM D1922   |
| TD                                       | 11             | g/μm     | ASTM D1922   |
| <b>Dart Impact F50</b>                   | 2              | g        | ASTM D1709   |
| <b>THERMAL PROPERTIES</b>                |                |          |              |
| <b>Vicat Softening Temperature</b>       | 92             | °C       | ASTM D1525   |

(1) Properties have been measured by producing 30 μm film with 2.5 BUR using 100% HP2023JN.

## PROCESSING CONDITIONS

Typical processing conditions for HP2023JN are:

Barrel temperature: 160 - 190°C

Blow up ratio: 2.0 - 3.0

## STORAGE AND HANDLING

Polyethylene resin should be stored in a manner to prevent a direct exposure to sunlight and/or heat. The storage area should also be dry and preferably do not exceed 50°C. SABIC would not give warranty to bad storage conditions which may lead to quality deterioration such as color change, bad smell and inadequate product performance. It is advisable to process PE resin within 6 months after delivery.

## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.